



James Briggs Ltd
Salmon Fields, Royton, Oldham OL2 6HZ UK
Tel: 0161 627 0101 Fax: 0161 627 0971
www.jamesbriggs.co.uk

TECHNICAL DATA SHEET

TRUCK BED LINER UK989

1. Introduction

A high quality single pack coating designed to deliver a tough durable finish to the load carrying areas of pick-up trucks. The textured finish also imparts anti-slip and abrasion resistant properties.

2. Where to use

- On pre-painted surfaces
- Metals
- Most plastics

3. Where not to use

- This product is specifically for use on load carrying areas.
- Very flexible surfaces.

4. Benefits

- Protection against load damage
- Impact Resistant
- Quick Drying
- Textured anti slip finish
- Prevention of corrosion

5. Physical properties [Product base except where stated].

Appearance	Black
pH	Not applicable
Specific Gravity	1.214 +/-0.015
Viscosity	5000cps max
Non Volatiles % m/m	40 – 50
Active Content % m/m, as supplied	20 – 30
Flammability, as supplied	Extremely flammable, flash point below -20°C
Composition Data, as supplied	A solution of a polyurethane resin, polypropylene beads in solvent composed predominantly of acetone, solvent naphtha and xylene propelled by a blend of propane and butane. (See SDS for full list of constituent solvents)
Volatile Organic Content, as supplied	Compliant with EU Directive 2004/42/CE
Coverage	Up to 0.5 sq m per 400ml
Service Temperatures	Up to 80°C.
Application Temperatures	10 - 25°C

6. Application Details

This information is provided in good faith based upon data and sources believed to be reliable and correct. Conditions of use, outside the control of the Company, dictate that no responsibility can be assumed for the ultimate performance of this product.



James Briggs Ltd

Salmon Fields, Royton, Oldham OL2 6HZ UK

Tel: 0161 627 0101 Fax: 0161 627 0971

www.jamesbriggs.co.uk

TECHNICAL DATA SHEET

**TRUCK BED LINER
UK989**

Ensure surfaces are clean, dry, and free from oils, traffic film, greases, tars etc. If necessary, wash the surface with a good quality detergent rinse thoroughly and dry with a cloth. Wipe over the surface with white spirit or thinners to remove any residual oil or grease. Mask the area to prevent overspray. Undertake a small test application on an inconspicuous area prior to use to ensure suitability for use.

Shake the can thoroughly for at least two minutes. Repeat shaking at regular intervals during use.

Apply an even coating from a distance of 30 – 40cm to avoid runs. Apply 1 to 2 coats as necessary to achieve total and even coverage, leaving at least 20- 30 minutes between each application.

Allow at least 24 hours after initial application before any further recoating.

On completion of use, invert can and depress actuator for a few seconds to prevent nozzle blockage.

7. Availability.

400ml Aerosols

PC976/RJB/August 2017