



James Briggs Ltd

Salmon Fields, Royton, Oldham OL2 6HZ UK Tel: 0161 627 0101 Fax: 0161 627 0971 www.jamesbriggs.co.uk

TECHNICAL DATA SHEET

ZINC PRIMER XUK207

1. Introduction

A zinc rich coating that dries to a smooth, metallic, grey matt finish, designed to provide outstanding corrosion resistance on ferrous surfaces, and an excellent receptive basis for subsequent decorative and functional finishes.

2. Where to Use

Designed for use on all types of cleaned metallic surfaces, particularly for protection of welds, and most conventional coatings.

3. Where not to use

• On some painted surfaces without first establishing suitability [see Section 6].

4. Benefits

- Provides a dry coating containing over 60% zinc metal.
- Provides exceptional anti-corrosive properties.
- Suitable for use on galvanised surfaces
- Suitable for exterior applications
- Outstanding resistance to salt spray, particularly applicable to coastal applications
- Outstanding resistance to weathering
- Suitable for welding through

5. Physical Properties [Zinc Primer base except where stated]

Appearance Dull metallic grey liquid with a strong organic odour

pH Not applicable
Specific Gravity 1.150 +/- 0.025
Non Voletiles % m/m 40 50

Non Volatiles % m/m 40 - 50Active Content % m/m, as supplied 20 - 30

Viscosity @ 20°C 500 – 2,500 cPs

Flammability, as supplied Extremely flammable, flash point below -20°C.

Composition Data, as supplied A solvent based solution of acrylic and alkyd resins, with micronised zinc pigments and a thixotrope in butane/isobutane/propane propellant

Volatile Organic Content, as supplied Compliant with EU Directive 2004/42/CE

Service Temperatures Up to 80°C Application Temperatures 15 - 25°C

6. Application Details

Prepare the area to be treated, ensuring freedom from dust, grime, greases, oils etc, using a detergent solution followed by rinsing thoroughly and drying. Rust, other surface contamination, and loosely adhering matter should be removed using a stiff brush or an appropriate grade of wet and dry abrasive cloth. Following preparation the surfaces should be further treated with a solvent wipe using HYCOTE BRAKE CLEANER, [XUK302], or white spirit and allow to dry.

Shake the can thoroughly for at least two minutes. Repeat shaking at regular intervals during use.





James Briggs Ltd
Salmon Fields, Royton, Oldham OL2 6HZ UK
Tel: 0161 627 0101 Fax: 0161 627 0971
www.jamesbriggs.co.uk

TECHNICAL DATA SHEET

ZINC PRIMER XUK207

Apply sparingly from a distance of 20 - 25cm. Apply typically 2 to 3 coats or as necessary to achieve total and even coverage, leaving between 10 - 15 minutes between each application.

Allow at least 24 hours between application of final coating and preparation for any subsequent finishes that may be required.

On completion of use, invert can and depress actuator for a few seconds to prevent nozzle blockage.

This product may be used with confidence over acrylic or cellulosic paints, and may be over-coated with acrylics, alkyds, cellulosics, p/u alkyds and epoxies. Where over-coating of a previously applied alkyd coating is suspected, always test for suitably of use by applying several coats in an inconspicuous area, and allow to dry thoroughly to establish absence of wrinkling and other surface defects.

7. Availability

400 ml. aerosols

B064670, August 2017.